

## WFGP Silver20 High Performance Mirror Film

Performance Data	Single Pane	<b>Double Pane</b>
<b>Total Solar Energy Rejection</b>	80%	70%
Solar Heat Gain Coefficient (G Value)	0.2	0.30
Visible Light Transmitted	18%	17%
Internal Reflection	58%	59%
UV Rejection	99%	99%
Glare Reduction	83%	79%

Silver20 High Performance Mirror window film provides excellent heat and glare rejection to create a more comfortable environment in which to work or relax. The solar reduction can also lower air conditioning consumption to save energy and by reducing the reflection on monitor screens, TVs and Tablets, eye-strain can be eased.

The rejection of harmful Ultra Violet rays, visible light and heat greatly reduces fading of fabrics and furnishings.

The exterior silver finish is ideal to create a one-way mirror effect in daylight hours to provide privacy of valuable assets, personal modesty or hide unattractive parts of a building.

## **Important Information**

Internal application only.

We do not recommend the use of internally installed solar reflective film on Georgian Wired glass or double-glazed units if they are Laminated glass due to the increased risk of thermal fracture.

Polyester film is not suitable for application to plastics or polycarbonates.

UV rays, visible light and heat are the main causes of fading. However, they are not the only causes. By reducing these elements fading can be greatly reduced but it is impossible to completely eliminate it.

One-way vision privacy is dependent upon the light ratio on either side of the filmed window. It can only be achieved when it is brighter outside than inside. That is why the film will only be effective during daylight hours.

Please Note: the above is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use, and the purchaser assumes all risks in connection with such use.



**2** 0345 337 4751



is a trademark of WF Glazing Protection Ltd



www.wfprotection.co.uk